

Dansand A/S

Lervejdal 8B
Postbox 39
DK-8740 Brædstrup

SIEVE ANALYSIS

Printed: 20-03-2009

Article no.: 0

Descr. of goods: Sand No. 0

Period: 01-01-2009 - 10-03-2009

Aperture size, mm	Amount on sieve		Amount through sieve		
	g	%	Max, %	Actual, %	Min, %
0,800	0,00	0,0		100,0	
0,710	6,30	6,4		93,6	
0,630	24,66	25,1		68,5	
0,500	53,94	54,9		13,7	
0,400	11,02	11,2		2,5	
0,000	2,41	2,5		0,0	
Total	98,33	100,0			

Oversize, %: 0,0 Max, %: 5,0 Undersize, %: 2,5 Max, %: 5,0

D90, mm: 0,699 D50, mm: 0,586 D20, mm: 0,515 D10, mm: 0,467

Dispersion (D60/D10): 1,305

Density, kg/m3: 2618 Bulk density, g/cm3: 1,586 Glow loss, %: 0,20

SiO₂, %: 99,300 Al₂O₃, %: 0,340 CaO, %: 0,010 Na₂O, %: 0,000
K₂O, %: 0,180 Fe₂O₃, %: 0,071 TiO₂, %: 0,020

